

MULTI FLUTE SHORT ROUGHING
- SIDE CUTTING

ESH751, ESH752 Series

ESH753, ESH762 Series

MATERIAL	CARBON STEELS ALLOY STEELS TOOL STEELS				CARBON STEELS ALLOY STEELS TOOL STEELS				CARBON STEELS ALLOY STEELS TOOL STEELS			
HARDNESS					~ HRc20				HRc20 ~ HRc30			
STRENGTH	~ 500N/mm²				500 ~ 800N/mm²				800 ~ 1000N/mm²			
DIAMETER	RPM	FEED	Vc	fz	RPM	FEED	Vc	fz	RPM	FEED	Vc	fz
6.0	1800	80	35	0.015	1600	60	30	0.013	1200	55	25	0.015
8.0	1400	105	35	0.025	1100	75	30	0.023	900	65	25	0.024
10.0	1100	150	35	0.034	900	120	30	0.033	800	110	25	0.034
12.0	900	180	35	0.050	800	140	30	0.044	630	110	25	0.044
14.0	800	180	35	0.056	700	140	30	0.050	560	110	25	0.049
16.0	700	180	35	0.064	560	140	30	0.063	450	110	25	0.061
18.0	630	180	35	0.071	500	140	30	0.070	400	110	25	0.069
20.0	560	180	35	0.080	450	140	30	0.078	400	110	25	0.069
22.0	500	220	35	0.088	450	170	30	0.076	350	140	25	0.080
25.0	450	220	35	0.098	400	170	30	0.085	310	140	25	0.090
28.0	400	210	35	0.088	350	160	30	0.076	280	130	25	0.077
30.0	350	210	35	0.100	310	160	30	0.086	250	130	25	0.087
32.0	350	210	35	0.100	280	160	30	0.095	220	130	20	0.098

MATERIAL	CARBON STEELS ALLOY STEELS TOOL STEELS				ALUMINUM ALUMINUM ALLOYS			
HARDNESS	HRc30 ~ HRc40							
STRENGTH	1000 ~ 1300N/mm²							
DIAMETER	RPM	FEED	Vc	fz	RPM	FEED	Vc	fz
6.0	800	30	15	0.013	4500	200	85	0.015
8.0	560	35	15	0.021	3100	230	80	0.025
10.0	450	60	15	0.033	2500	350	80	0.035
12.0	400	70	15	0.044	2000	400	75	0.050
14.0	350	70	15	0.050	1800	420	80	0.058
16.0	280	70	15	0.063	1600	450	80	0.070
18.0	250	70	15	0.070	1400	470	80	0.084
20.0	220	70	15	0.080	1200	500	75	0.104
22.0	220	85	15	0.077	1100	470	75	0.085
25.0	180	85	15	0.094	1000	450	80	0.090
28.0	160	85	15	0.089	900	510	80	0.094
30.0	160	85	15	0.089	900	530	85	0.098
32.0	140	85	15	0.101	800	500	80	0.104

RPM = rev./min.
Feed = mm/min.
Vc = m/min.
fz = mm/tooth



*The FEED, in long & extra long types, should be reduced by around 50%