

					TRE30, TRE31, TRE32 TRE33, TRE34	TRJ15, TRJ16 TRJ17, TRJ18
ISO	VDI 3323	Material Description	HB	HRc	Vc (m/min.)	
P	1	Non-alloy steel	125		5-20	15-45
	2		190	13	10-50	10-55
	3		250	25	10-50	10-55
	4		270	28	15-40	15-50
	5		300	32	15-40	15-50
	6	Low alloy steel	180	10	8-30	8-30
	7		275	29	8-30	8-30
	8		300	32	8-30	8-30
	9		350	38	8-30	8-30
	10	High alloyed steel, and tool steel	200	15	8-30	8-30
	11		325	35	8-30	8-30
M	12	Stainless steel	200	15	5-15	8-20
	13		240	23	5-15	8-20
	14		180	10	5-15	8-20
K	15	Grey cast iron	180	10	15-35	15-35
	16		260	26	15-35	15-35
	17	Nodular cast iron	160	3	15-35	15-35
	18		250	25	15-35	15-35
N	21	Aluminum-wrought alloy	60		15-35	15-35
	22		100		15-35	15-35
	23	Aluminum-cast, alloyed	75		15-35	15-35
	24		90		15-35	15-35
	25		130		15-35	15-35
	26		110		15-35	15-35
	27	Copper and Copper Alloys (Bronze / Brass)	90		15-35	15-35
	28		100		15-35	15-35